



## Finger-Jointed Structural Timber

Date: 02/2021

Made from spruce in visual and industrial quality. Visual qualities are made from scandinavian sawn wood. Additional dimensions and wood species on request.

		Width [mm]												
		80	95	100	120	140	145	160	180	200	220	240	260	280
Height [mm]	40													
	45													
	60													
	80													
	100													
	120													

Industrial
  Visual

### Product properties

Harmonized standard	DIN EN 15497:2014
Strength class	C 24
E-Modulus	11.000 N/mm <sup>2</sup>
Bending strength	24 N/mm <sup>2</sup>
Moisture content	≤ 18 %
Service class	1 + 2



Mechanical properties of strength class C 24 according to DIN EN 338:2009