



Glued Solid Timber

Date: 02/2021

Duobalken / Triobalken

Made from spruce in visual and industrial quality. Visual qualities are made from nordic sawn wood. Additional dimensions and wood species on request.

		Width [mm]													
		100	120	140	160	180	200	220	240	260	280				
Height [mm]	100	Industrial	Industrial	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	120		Industrial	s	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	140				Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	160					Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	180						Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	200							Visual	s	Visual	s	Visual	Visual	Visual	Visual
	220											Visual	Visual	Visual	Visual
	240												s	Visual	Visual

Industrial

Visual

s

Special dimension

Product Characteristics

Harmonized Standard	DIN EN 14080:2013
Strength Class	C 24
E-Modulus	11.000 N/mm ²
Bending Strength	24 N/mm ²
Moisture Content	≤ 15 %
Service Class	1 + 2



Mechanical properties of strength class C 24
according to DIN EN 338:2009