



Glued Solid Timber

Date: 09/2022

Duobalken / Triobalken

Made from spruce in visual and industrial quality. Visual qualities are made from nordic sawn wood. Additional dimensions and wood species on request.

		Width [mm]													
		100	120	140	160	180	200	220	240	260	280				
Height [mm]	100	Industrial	Industrial	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	120	Industrial	Industrial	s	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	140	Industrial	Industrial	Industrial	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	160	Industrial	Industrial	Industrial	Industrial	Visual	Visual	s	Visual	s	Visual	Visual	Visual	Visual	Visual
	180	Industrial	Industrial	Industrial	Industrial	Industrial	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual	Visual
	200	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	s	Visual	s	Visual	Visual	Visual	Visual	Visual
	220	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial
	240	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	Industrial	s	Visual	Visual	Visual	Visual	Visual

Industrial

Visual

s

Special dimension

Product Characteristics

Harmonized Standard	DIN EN 14080:2013
Strength Class	C 24
E-Modulus	11.000 N/mm ²
Bending Strength	24 N/mm ²
Moisture Content	≤ 15 %
Service Class	1 + 2



Mechanical properties of strength class C 24
according to DIN EN 338:2009